

DURA PRO[®] **AW0024**

LIQUID POLYURETHANE ADHESIVE

Key Properties

- Excellent adhesion to Variety of Substrates
- Very good temperature, moisture and aging reistance
- Passes ASTM D1183 test
- 10 minute press time

Recommended Use Areas

- Designed for the production of Engineered Wood components
- Designed for extrusion and closed roll-coater systems

Typical Properties

ADHESIVE TYPE:	Polyurethane
TYPICAL VISCOSITY:	6,000 cps ± 2,000 cps
SPECIFIC WEIGHT:	9.3 lbs/gallon
OPEN TIME:	5 minutes
PRESS TIME:	10 minutes
APPLICATION TEMPERATURE:	Ambient
COLOR: Room temp.	Tan liquid
VOC CONTENT, (g/L):	0
SHELF LIFE:	6-12 Months

Packaging

250 gallon Non-returnable totes
55 gallon closed head drums
5 gallon pails closed head pails
300 ml aluminium cartridge

Service products

DURA-PUR[®] UC 2045 for daily cleaning of roll-coater and purging of application and delivery system

Our personnel are available to help purchasers obtain best results from our products, and recommendations are based on tests and information believed to be reliable. However, since we have no control over the conditions under which our products are transported to, stored, handled, or used by purchasers, all recommendations and sales are made on condition that we will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.
Rev: 01/24/06